

**PT ZEFA VALINDO JAYA**

Komplek Ruko Harapan Indah  
Blok EC No. 10 - 11 Bekasi 17131  
Phone : +6221 8873531, 88865553-54, 88977065  
Fax : +6221 8873532  
e-mail : info@zevanya.com  
Website : www.zevanya.com

**KAMOME SG PINK**

No. 5205  
Jan '10  
CPI

**KAMOME SG PINK** is an Erodible anti-fouling paint which is formulated for protection of underwater surfaces of wooden boat and steel ship's bottom against fouling and marine organism.

**TECHNICAL DATA**

Type :	Erodible anti-fouling paint				
Recommended Use :	Antifouling paint on wood and steel ship's bottom for worldwide service with extended dry-docking interval.				
Color :	Pink				
Flash Point :	23°C				
Volume Solid :	52 ± 2%				
Coverage(Theoretical) :	0.095 – 0.190 L/m <sup>2</sup> ; 179 – 357 gr/m <sup>2</sup>				
Wet Film Thickness :	3.8 – 7.6 mils ; 95 – 190 μ				
Dry Film Thickness :	2.0 – 4.0 mils ; 50 – 100 μ				
Drying Time :	Temperature	5°C	10°C	20°C	30°C
(at D.F.T. 100 μ)	Surface Dry	3 hrs.	2 hrs.	1 hr.	30 min.
	Hard Dry	12 hrs.	8 hrs.	5 hrs.	4 hrs.
Painting Interval :	Minimum	12 hrs.	8 hrs.	5 hrs.	4 hrs.
(at D.F.T. 100 μ)	Maximum	-	-	-	-
Dry to Launch :	Minimum	22 hrs.	16 hrs.	10 hrs.	8 hrs.
(at D.F.T. 100 μ)	Maximum	-	-	-	-
Thinner :	RAVAX THINNER				
Method of Application :	Airless Spray, Brush, Roller				
Condition of Application :	Temperature	Minimum 0°C			
	Humidity	Maximum 85% R.H.			
	For Airless Spray ;				
	Tip No.	GRACO 621(721)-633(733)			
	Nozzle Pressure	120 – 150 Kg/cm <sup>2</sup>			
	Viscosity	90 sec. (Ford Cup No. 4)			
	Thinning	0 – 5% by volume			
Preferable Preceding Coats :	-				
Preferable Subsequent Coats :	-				
Packaging :	One pack product				