

P.T. SUPERINTENDING COMPANY OF INDONESIA

No. : 1945545

Page No. : 2 of 2

REPORT OF ANALYSIS

Parameter	Unit	Result	Method
Aluminium Trioxide (Al <sub>2</sub> O <sub>3</sub> )	%	0.68	AAS
Iron Trioxide (Fe <sub>2</sub> O <sub>3</sub> )	%	0.31	AAS
Chrome Trioxide (Cr <sub>2</sub> O <sub>3</sub> )	%	0.02	AAS
Loss on Ignition (LOI)	%	0.15	Gravimetri
Potassium Oxide (K <sub>2</sub> O)	%	0.01	AAS
Calcium Oxide (CaO)	%	0.48	AAS
Magnesium Oxide (MgO)	%	Below 0.01	AAS
Manganium Dioxide (MnO <sub>2</sub> )	%	Below 0.01	AAS
Sodium Oxide (Na <sub>2</sub> O)	%	0.02	AAS
Silicone Dioxide (SiO <sub>2</sub> )	%	97.96	Gravimetri
Titanium Dioxide (TiO <sub>2</sub> )	%	0.33	Spectrofotometric

Sucofindo Laboratory,



Drs. ACE TAKHRUDIN  
NPP. 92.66.03570

A. B. H. M.  
15

This inspection report has been prepared and this certificate/report is issued subject to the Standard General Conditions of the INTERNATIONAL FEDERATION OF INSPECTION AGENCIES (IFIA). The company's liability is limited under the terms of Article 10 thereof. Issuance of this certificate/report does not exonerate the buyers and sellers from exercising all their rights and discharging their liabilities under the Contract of sale.